100% dielectric gratings offer unbeatable environmental and thermal stability combined with high efficiency, low PDL performance



Polarization independent (PING) telecom gratings from Ibsen are produced by holographic/lithographic stepper technology in 100% dielectric materials. This leads to unbeatable thermal and environmental stability, with no polymers, epoxies, gelatins or metals in the optical path nor in the grating whatsoever.

Advanced etching technology ensures highest diffraction efficiency and lowest PDL over a very broad bandwidth. Low angular sensitivity is an added bonus for module design and assembly.

## **PING Grating**

1765 I/mm PING for 850 nm band PING-1765-025

#### 1765 I/mm PING for Telecom C-band PING-1765-025

#### **Benefits**

High efficiency, low PDL, broad spectral bandwidth


Transmission gratings give much greater alignment tolerances

Low transmitted wavefront distortion

High tolerance to illumination angle of incidence

Two grating designs are possible, offering compact design possibilities

Unbeatable thermal & environmental stability & lifetime



Parameter	Specification
Materials	100% dielectric materials
Grating area	25 mm x 16 mm
Chip size	29.5 mm x 20 mm
Chip thickness	3 mm
Grating resolution	1765 l/mm
PDL	<0.5 dB
Angle of incidence (AOI)	49.9 degrees
Diffraction efficiency (TE & TM)	>80%
Bandwidth	795 nm – 885 nm
Production technology	Holographic/lithographic stepper and RIE etching
Maximum operating temperature	>500 degrees C
Pagkaging and shipment	Gelpak containers. Manufactured and sealed in class 10 cleanroom
Cleaning recommendation	First contact. Available from Photonic Cleaning




For further information you can contact us directly at:

Ibsen Photonics A/S Phone +45 4434 7000 Ryttermarken 17 Fax +45 4434 7001 DK-3520 Farum www.ibsen.com

Denmark E-mail inquiry@ibsen.com


### 1765 I/mm PING for 850 nm band PING-1765-025

#### **Typical Grating Performance**



#### 800/850 nm band PING Typical Diffraction Efficiency

#### **Diffraction Efficiency vs Incidence Angle**



Ibsen photonics For further information you can contact us directly at:


Ibsen Photonics A/S Phone +45 4434 7000

Ryttermarken 17 Fax +45 4434 7001 DK-3520 Farum www.ibsen.com


Denmark E-mail inquiry@ibsen.com

# 600 I/mm PING for Telecom C-band PING-600-045

#### **Configuration/Definitions**



#### Drawing



Specifications are subject to change without notice.

The above grating is an example of Ibsen's capabilities. Ibsen operates as grating partner for our customers, from being an integrated part of the grating and device / instrument design phase, to the manufacturing of prototypes, to volume manufacturing of OEM gratings.

Ibsen photonics For further information you can contact us directly at:

 Ibsen Photonics A/S
 Ryttermarken 17

 Phone +45 4434 7000
 Fax +45 4434 7001

DK-3520 Farum www.ibsen.com Denmark E-mail inquiry@ibsen.com